

Ni-Cr-Fe Welding Electrode

INCONEL® Welding Electrode 182



9

INCONEL Welding Electrode 182 is used for shielded-metal-arc welding of INCONEL alloys 600 and 601. The weld metal has excellent high-temperature strength and oxidation resistance and can meet stringent radiographic requirements.

Dissimilar welds for which the electrode are used include INCONEL alloys and INCOLOY alloys joined to carbon steels, stainless steels, nickel and MONEL alloys, MONEL alloys joined to carbon steels; nickel joined to stainless steels; and stainless steels joined to carbon steels.

The electrodes provide excellent operability for groove and fillet welding in the downhand position and the smaller diameter electrodes are also suitable for all position welding. Power supply: direct current, electrode positive.

Specifications

AWS A5.11 ENiCrFe-3 (UNS W86182)
 ASME II, Part C, SFA-5.11, ENiCrFe-3 (UNS W86182)
 ASME IX, F-No.43
 *DIN 1736 EL-NiCr15FeMn (2.4807)
 *(EN) ISO 14172 – ENi6182 (NiCr15Fe6Mn)
 *Supply to these specifications available upon request
 For manufacture to ASME III (NCA3800, NB2400), MIL, and other specifications please refer your inquiry to the Technical Department prior to order placement.

Approvals

Canadian Welding Bureau
 VdTUV 2105.01
 Other approvals may be applicable. Please confirm details of current scope of approvals with the Technical Department prior to order placement.

Limiting Chemical Composition	Ni+Co		Cu	
	59.0 min.	0.50 max.
C	0.10 max.	Cr
Mn	5.0-9.5	Ti
Fe	10.0 max.	Nb+Ta
S	0.015 max.	P
Si	1.0 max.	Others

Minimum Mechanical Properties	Tensile Strength, psi		80,000
		MPa	552
	Elongation, (4d) %		30

Available Product Forms – Supplied in 10lbs (4.54kg) hermetically sealed containers

Diameter	mm in	2.4 3/32	3.2 1/8	4.0 5/32	4.8 3/16
Length	mm in	229 12	356 14	356 14	356 14
Current (DC+)	A	40-65	65-95	95-125	125-165

INCONEL® Welding Electrode 182